



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 472 946 B1

(12)

EUROPEAN PATENT SPECIFICATION

(43) Date of publication of patent specification: 15.11.95 (51) Int. Cl.⁶: C08F 297/08

(21) Application number: 91112955.9

(22) Date of filing: 01.08.91

(64) Elastoplastic polyolefin compositions.

(30) Priority: 01.08.90 IT 2116990

(43) Date of publication of application:
04.03.92 Bulletin 92/10

(45) Publication of the grant of the patent:
15.11.95 Bulletin 95/46

(84) Designated Contracting States:
AT BE DE ES FR GB IT NL SE

(56) References cited:
EP-A- 0 077 532 EP-A- 0 086 300
EP-A- 0 170 255 EP-A- 0 373 660
EP-A- 0 400 333 EP-A- 0 444 671

(73) Proprietor: MONTELL NORTH AMERICA INC.
2801 Centerville Road
New Castle County
Delaware (US)

(72) Inventor: Cecchin, Giuliano
2, via U. Foscolo
I-44100 Ferrara (IT)
Inventor: Guglielmi, Floriano
96, via Aeroporto
I-44100 Ferrara (IT)
Inventor: Pelliconi, Anteo
16, via E. Fermi, S.M. Maddalena
I-44020 Ro,
Ferrara (IT)
Inventor: Burgin, Emanuele
21, via Predosa
I-40069 Zola Predosa,
Bologna (IT)

(74) Representative: Zumstein, Fritz, Dr. et al
Patentanwälte,
Dr. F. Zumstein,
Dipl.-Ing. F. Klingseisen,
Bräuhausstrasse 4
D-80331 München (DE)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 472 946 B1

Description

The present invention concerns highly flexible elastoplastic polyolefin compositions and the process for their preparation.

5 It is known that one can obtain polyolefin compositions having elastic properties while maintaining a good thermoplastic behavior (i.e., that can be transformed into finished products with the same techniques used for thermoplastic polymers), by way of sequential copolymerization of propylene, optionally containing minor quantities of olefin comonomers, and then ethylene/propylene or ethylene/ α -olefin mixtures.

10 Catalysts based on halogenated titanium compounds supported on magnesium chloride are used for this purpose.

Given the increasing practical interest for this type of compositions, due, among other things, to the valued properties which are typical of polyolefins (such as chemical inertia, mechanical properties and nontoxicity), there is an increasing effort in the art to extend the use of said compositions to many different fields.

15 European published patent application 400333 describes elastoplastic polyolefin compositions obtained by sequential polymerization comprising:

- A) 10-60 parts by weight of a crystalline polymer or copolymer of propylene;
- B) 10-40 parts by weight of a polymer fraction containing ethylene, insoluble in xylene at ambient temperature;
- 20 C) 30-60 parts by weight of an ethylene/propylene copolymer fraction, soluble in xylene at ambient temperature.

Said compositions are flexible and have valued elastic properties, as demonstrated by low flexural modulus values (less than 700 MPa, and, typically, higher than 200 MPa) associated to good tension set values, but do not have particularly good optical characteristics (transparency).

25 It has also been found that good transparency characteristics can be obtained in compositions prepared by sequential polymerization when the content of crystalline polymer produced in the first stage of polymerization is relatively high, to the detriment of elasticity and flexibility properties.

For example, published European patent application 373660 describes polypropylene compositions obtained by sequential polymerization, containing (A) from 70 to 98% by weight of a crystalline copolymer of propylene and (B) from 2 to 30% by weight of an elastomeric copolymer of ethylene with propylene and/or another α -olefin whose portion soluble in xylene has an intrinsic viscosity which satisfies a particular correlation with the one of the crystalline copolymer.

This compositions, however, although they have good optical qualities, also have a high flexural modulus (typically higher than 600 MPa), given the high content of crystalline copolymer (A).

35 Therefore, there is a need for elastoplastic polyolefin compositions which are even more flexible (i.e., they have lower flexural modulus values) than the products already available. It is also desirable that said compositions have good optical qualities.

In fact, flexible polymer materials are used widely for a variety of applications, such as the medical field (for example in the production of containers for plasma or intravenous solutions, or phlebotomy tubes), as well as for packaging, for calendared materials or to extrusion coat or cover electrical wires and cables.

In many of this applications vinyl chloride polymers containing adequate plasticizers, which are necessary to give said polymers their desired flexibility characteristics, are presently used.

Said polymer products, however, are subject to ever increasing criticism both for the suspected toxicity of the plasticizers they contain and because when incinerated, they can disperse into the atmosphere 45 extremely toxic by-products, such as dioxin.

It would be very useful, therefore, to substitute said materials with products which besides the desired flexibility characteristics and, optionally, transparency, would have the chemical inertia and nontoxicity typical of olefin polymers.

This invention provides a highly flexible elastoplastic polyolefin composition comprising, in parts by 50 weight:

- A) 10-50, preferably 10-40 and more preferably 20-35 of homopolymer of propylene with isotactic index greater than 80, preferably from 85 to 98, or of a copolymer of propylene with ethylene, a $\text{CH}_2 = \text{CHR}$ α -olefin where R is a 2-8 carbon alkyl radical or a combination thereof, which copolymer contains over 85%, preferably from 90 to 99% by weight of propylene, and has an isotactic index higher than 80;
- 55 B) 5-20, preferably 7-15, of a copolymer fraction containing ethylene, insoluble in xylene at ambient temperature;
- C) 40-80, preferably 50-70, of a copolymer fraction of ethylene and (i) propylene or (ii) another $\text{CH}_2 = \text{CHR}$ α -olefin, where R is a 2-8 carbon alkyl radical, or (iii) a combination thereof, optionally, with

minor amount of a diene, containing less than 40% by weight, preferably 20-38%, more preferably 25-38% by weight of ethylene, said fraction being also soluble in xylene at ambient temperature, and having an intrinsic viscosity from 1.5 to 4 dl/g, preferably from 1.7 to 3 dl/g;

with a percentage by weight of the sum of the (B) and (C) fractions with respect to the total polyolefin composition from 50% to 90%, preferably from 65% and 80%, and a (B)/(C) weight ratio lower than 0.4, preferably from 0.1 to 0.3.

The total quantity of copolymerized ethylene is preferably from 15% to 35% by weight.

The compositions present at least one melt peak, determined by way of DSC, present at a temperature higher than 120 °C, and at least one peak, relative to the vitreous transition, present at temperatures from -10 °C and -35 °C.

Said compositions, moreover, have a flexural modulus of less than 150 MPa, generally from 20 and 100 MPa; yield point from 3 to 20 MPa tensile stress at break, and elongation at break respectively from 10 to 20 MPa, and higher than 400%; a tension set, at 75% elongation, from 20% to 50%; Shore D hardness from 20 and 35; moreover, they do not break when an IZOD impact test is conducted at -50 °C. Preferably the Haze values are less than 40%.

Copolymers of propylene with ethylene or an α -olefin are or a combination thereof preferred (A) components, because they confer high transparency to the compositions of the invention.

The compositions can be prepared with a polymerization process comprising at least two stages, where in the first stage the relevant monomer(s) are polymerized to form component (A) and in the following stages the mixtures ethylene-propylene, ethylene and another α -olefin, ethylene-propylene-another α -olefin and, optionally, a diene, are polymerized to form components (B) and (C).

The polymerization can be carried out in a liquid phase, a gas phase or a liquid-gas phase.

For example, it is possible to carry out the propylene polymerization stage using liquid propylene as diluent, and the following copolymerization stage in gas phase, without intermediate stages except for the partial degassing of the propylene.

The propylene polymerization to form component (A) can be done in the presence of ethylene or an α -olefin, such as for example butene-1, pentene-1, 4-methylpentene-1, hexene-1 and octene-1, or combinations thereof in such quantities that the isotactic index of the resulting component (A) is not less than 80%.

As previously said, the copolymerization of propylene and ethylene or another α -olefin or combinations thereof to form components (B) and (C) can be carried out in the presence of a diene, conjugated or not, such as butadiene, 1,4-hexadiene, 1,5-hexadiene and ethylidene-norbornene-1.

The diene when present, is typically in an amount of from 0.5 to 10% by weight with respect to the weight of (B) + (C).

The reaction temperature in the polymerization stage for the preparation of component (A) and in the one for the preparation of components (B) and (C) can be the same or different, and is usually from 40 °C to 90 °C, preferably 50-80 °C for the preparation of component (A), and 40-60 °C for the preparation of components (B) and (C).

The pressure of the first stage, if carried out in liquid monomer, is the one which competes with the vapor pressure of the liquid propylene at the operating temperature used, and is possibly modified by the vapor pressure of the small quantity of inert diluent used to feed the catalyst mixture, and the overpressure of optional monomers and the hydrogen used as molecular weight regulator.

The polymerization pressure, if done in liquid phase, indicatively can be from 5 to 30 atm. The residence times relative to the two stages depend on the desired ratio between fraction (A) and (B) + (C), and are usually from 15 min. to 8 hours. As molecular weight regulators one can use the traditional chain transfer agents known in the art, such as hydrogen or ZnEt_2 .

The catalyst used in the polymerization comprises the product of the reaction of a solid component containing a titanium compound and an electron-donor compound (internal donor) supported on magnesium chloride, with an Al-trialkyl compound and an electron-donor compound (external donor).

In order to obtain the compositions of the invention in flowable spherical particles having high bulk density, it is critical that the solid catalyst component present the following properties:

- surface area less than 100 m²/g, preferably from 50 to 80 m²/g.
- porosity: from 0.25 to 0.4 cc/g.
- X-ray spectrum: Presence of halo at 2 θ angles from 33.5° and 35°, and absence of reflections at 2 θ = 14.95°.

The catalyst component is prepared with the following methods.

A magnesium chloride adduct with alcohols, containing generally 3 moles alcohol per mole MgCl_2 , is obtained in spherical particles by emulsifying the adduct, in the molten state, in an inert hydrocarbon liquid immiscible with the adduct, and then cooling the emulsion very quickly in order to cause a solidification of

the adduct in spherical particle form.

The particles then undergo a partial dealcoholation by way of a heating cycle at temperatures from 50 ° and 130 ° C, which brings the alcohol content from 3 to 1-1.5 moles per mole $MgCl_2$.

The adduct is then suspended in cold $TiCl_4$ (typically at 0 ° C), at a concentration of 40-50 g/l, and then brought to 80 ° - 135 ° C where it is maintained for 1 - 2 hours.

An electron-donor compound preferably selected from the alkyl, cycloalkyl or aryl phthalates, such as, for example, diisobutyl, di-n-butyl and di-n-octyl phthalate, is added to the $TiCl_4$.

The excess $TiCl_4$ is separated out by way of filtration or sedimentation, and the treatment with $TiCl_4$ is repeated one or more times; afterwards, the solid is washed with heptane or hexane and then dried.

The catalyst component thus obtained presents the following characteristics:

- surface area less than 100 m^2/g , preferably from 50 to 80 m^2/g .
- porosity: from 0.25 to 0.4 cc/g.
- a pore volume distribution wherein more than 50% of said pores have a radius greater than 100 Å.
- X-ray spectrum: presence of halo with maximum intensity at 2θ angles from 33.5° and 35°, and where there is no reflection at $2\theta = 14.95^\circ$.

The catalyst is obtained by mixing such catalyst component with an al-trialkyl compound, in particular Al-triethyl and Al-triisobutyl, and an electron-donor compound preferably selected from the silane compounds of the formula $R'R''Si(OR)_2$ where R' and R'' are the same or different, and are C_{1-18} alkyl, C_{3-18} cycloalkyl or C_{6-18} aryl radicals, and R is a C_{1-4} alkyl radical.

Representative silanes are diphenyldimethoxysilane, dicyclohexyldimethoxysilane, methyl-tert-butyldimethoxysilane, diisopropyldimethoxysilane, dicyclopentyldimethoxysilane, cyclohexylmethyldimethoxysilane.

Silane compounds such as phenyltriethoxysilane may also be used.

The Al-Ti ratio is generally from 10 to 200 and the silane/Al molar ratio from 1/1 to 1/100.

The catalysts may be precontacted with small quantities of olefin (prepolymerization), maintaining the catalyst in suspension in a hydrocarbon solvent, and polymerizing at temperatures from ambient to 60 ° C, thus producing a quantity of polymer from 0.5 to 3 times the weight of the catalyst.

The operation can also take place in liquid monomer, producing, in this case, a quantity of polymer 1000 times the weight of the catalyst.

By using the above mentioned catalysts the polyolefin compositions are obtained in spheroidal particle form, said particle having an average diameter from about 0.5 to 7 mm.

The products which can be obtained from the polyolefin compositions of the present invention find application particularly in the medical, automotive, packaging and electrical cable covering fields, as well as the calendering material field.

One can also add additives, fillers and pigments commonly used for olefin polymers, such as, for example, nucleating agents, extension oils, mineral fillers, organic and inorganic pigments.

The data reported in the examples and the specification relative to the following properties have been determined according to the methods indicated below.

<u>Property</u>	<u>Method</u>
5 - Melt Flow Note (MFRL.)	ASTM-D 1238 conditon L
- Ethylene % by weight	I.R. Spectroscopy
10 - Intrinsic viscosity	Determined in tetrahydro- naphthalene at 135°C
- xylene soluble % by weight	(see note below)
15 - Flexural modulus at 23°C and vitreous transition temperature (Tg)	Determined by way of a device for dynamic- mechanical measurements DMTA of Polymer Laboratories under the 25 following conditions: frequency measure: 1 Hz;
30	
35	
40	
45	
50	
55	

scanning temperature:

2°C/min.

The polymer sample to be analyzed is made up of a 40x10x2 mm plaque taken from a sheet obtained by pressure molding with Carver press at 200°C, 10 tons (of pressure) for 10 minutes, and cooling at 15°C/min.

25	- Notched IZOD impact	ASTM - D 256
	- Haze	ASTM - D 1003
30	- Shore Hardness D	ASTM - D 2240
	- Tension set at 75%	ASTM - D 412
35	- Tensile strength at break and at yield	ASTM - D 638
40	- Surface area	B.E.T.
	- Porosity	B.E.T.
45	- Bulk density	DIN - 53194

Unless otherwise specified, the samples to be subjected to the various physical-mechanical analyses were molded by use of a Negri & Bossi injection press 90, after stabilizing the sample with IRGANOX^R 1010 hindered phenolic stabilizer (0.1% by weight), and BHT (2,6 di-tert-butyl-p-cresol) (0.1% by weight), and pelletizing the sample with a single screw Bandera extruder (cylinder diameter 30 mm) at 210°C. The conditions were as follows:

- temperature of the melt 250 °C;
- temperature of the mold 60 °C;
- injection time 20 sec;
- cooling time 25 sec.

The samples to be subjected to the haze analysis were molded by way of a GBF G 235/90 injection press under the following conditions:

- temperature of the melt 260 °C;

- temperature of the mold 40 °C;
- injection time 20 sec.;
- cooling time 10 sec.

The dimensions of the samples for the haze test are 75x75x1 mm.

5 The weight percentage of the sum of the (B) and (C) fractions, indicated with % (B + C), is calculated by determining the weight of the mixture fed during the second stage and comparing it with the weight of the final product.

The weight percentage (%) of the (A), (B) and (C) fractions described in the text are determined in the following manner:

10

$$\% (A) = 100 - \% (B + C)$$

$$\% (C) = SF \cdot P_A S_A$$

15 where S_F and S_A are the percentage by weight of the portion soluble in xylene of the final product and of the fraction (A), respectively; P_A is the weight ratio between said fraction (A) and the final product.

$$\% (B) = 100 - \% (A) - \% (C)$$

20 The percentage by weight of ethylene contained in copolymer fraction (C) which is soluble in xylene is calculated using the following formula:

$$C_F - C_A \cdot X$$

25

$$\% \text{wt ethylene in fraction (C)} = \frac{\text{-----}}{\text{-----}}$$

$$1 - X$$

30 where:

C_F = % ethylene in the soluble in xylene of the final product;

C_A = % ethylene in the soluble in xylene of the fraction (A);

$$X = S_A \cdot P_A / S_F$$

The intrinsic viscosity of fraction (C) (I.V._c) has been calculated using the following formula:

35

$$(I.V._c) = (I.V._{SF} - I.V._A \cdot X) / (1 - X)$$

where:

- I.V._{SF} is the intrinsic viscosity of the fraction soluble in xylene of the final composition;

40

I.V._A is the intrinsic viscosity of the soluble in xylene of fraction (A).

Note

DETERMINING THE PERCENTAGE OF SOLUBLE IN XYLENE

45

2.5 g of polymer are dissolved in 250 ml of xylene at 135 °C under agitation. After 20 minutes the solution is cooled to 25 °C, with agitation, and then it is allowed to settle for 30 minutes.

The precipitate is filtered with filter paper; the solution is evaporated under a nitrogen current, and the residue dried under vacuum at 80 °C until reaches constant weight. The weight percentage of polymer soluble in xylene at ambient temperature is then calculated. The percent by weight of polymer insoluble in xylene at ambient temperature is considered the isotactic index of the polymer. This value corresponds substantially to the isotactic index determined by extraction with boiling n-heptane, which by definition constitutes the isotactic index of polypropylene.

55

EXAMPLES

GENERAL OPERATING CONDITIONS

5 The tests are done in a 22 l itres stainless steel autoclave equipped with a helicoid magnetic agitator, operating at about 90 rpm.

The gas phase is analyzed continuously with a process gaschromatograph in order to determine the content of ethylene, propylene and hydrogen. During polymerization, ethylene, propylene and hydrogen are fed in such a way that their concentration in gas phase is maintained constant.

10 The operation is discontinuous in two stages: the first stage is the polymerization of propylene with ethylene in liquid monomer and the second the copolymerization of ethylene and propylene in gas phase.

a) 1st stage:

15 In the autoclave at 20 °C are introduced, in order: 16 litres of liquid propylene, appropriate quantities of ethylene and hydrogen, as set forth in Table 1A, and the catalyst complex, consisting of a solid component (about 0.15 g) prepared as described below, and a mixture of 75 ml of Al-triethyl (TEAL) at 10% concentration in hexane and an appropriate quantity of cyclohexylmethyldimethoxysilane (CMMS) donor, so that the (Al/CMMS molar ratio = 7,5). The catalyst system is fed into the autoclave with propylene pressure. The temperature is brought to 70 °C in about 10 minutes and maintained constant throughout the entire polymerization process.

20 After a predetermined time period, essentially all the unreacted monomer(s) are eliminated by way of degassing at 60 °C at atmospheric pressure.

B) 2nd stage:

25 After a sample is removed in order to carry out the various analyses, the polymer of the first stage is brought to a temperature that has been predetermined. Then are fed, in order, propylene and ethylene at the ratio and in the quantity desired for to achieve the composition of the gas phase and the preestablished pressure.

30 During polymerization, the pressure and gas phase composition are maintained constant by feeding an ethylene-propylene mixture with the same composition of the desired copolymer, by way of instruments which regulate and/or measure the flow rate. The length of the feed depends on the reactivity of the catalyst system and the quantity of copolymer to be produced.

At the end of the polymerization, the particulate polymer is discharged, stabilized as set forth herein above and dried in an oven under nitrogen current at 60 °C. The catalyst component used is made from a $MgCl_2 \cdot 3 C_2H_5OH$ adduct prepared as follows:

35 28.4 g of anhydrous $MgCl_2$, 49.5 g of pure anhydrous ethanol, 100 ml of ROL OB/30 vaseline oil and 100 ml of silicone oil (350 cs viscosity) are introduced in a flask immersed in a bath thermoregulated, at 120 °C under agitation, in an inert atmosphere, until the $MgCl_2$ is completely dissolved. The mixture is then transferred hot, always under an inert atmosphere, in a 150 ml container equipped with a heating jacket, and containing 150 ml of vaseline oil and 150 ml of silicone oil. The mixture is maintained at 120 °C and under agitation, the latter being carried out with a Hanke & Kunkel K.G. Ika Werke Ultra
40 Turrax T-45 N agitator. Said agitation continues for 3 minutes at 3000 rpm. The mixture is discharged into a 2 liter vessel containing 1000 ml of anhydrous n-heptane stirred and cooled so that the final temperature does not exceed 0 °C. The $MgCl_2 \cdot 3EtOH$ microspheres thus obtained are filtered and dried under vacuum at ambient temperature. The dried adduct obtained in this manner is then dealcoholated by heating it at temperatures which increase gradually from 50 °C to 100 °C under nitrogen current until
45 the alcohol content is 1.5 moles per mole $MgCl_2$.

The partially dealcoholated adduct has a surface area = 9.1 m²/g and bulk density = 0.564 g/cc.

50 25 g of said adduct are added, under agitation at 0 °C, to 625 ml of $TiCl_4$. The mixture is then heated to 100 °C in 1 hour. When the temperature reaches 40 °C, diisobutylphthalate is added in an amount such that the Mg/diisobutylphthalate molar ratio = 8. The resulting mixture is heated at 100 °C for 2 more hours, then allowed to settle, and the liquid is syphoned off hot. 550 ml of $TiCl_4$ are added and the mixture is heated at 120 °C for 1 hour.

It is allowed to settle and the liquid is siphoned off hot. The solid is washed 6 times using 200 ml of anhydrous hexane at 60 °C, and three more times using 200 ml of anhydrous hexane at ambient temperautre. After drying under vacuum, the solid presents the following characteristics:

- 55
- porosity = 0.261 cc/g;
 - surface area = 66.5 m²/g;
 - bulk density = 0.55 g/cc.

All the analyses performed and relative operating conditions are shown in Tables 1A and 1B.

Table 1A

Examples		1	2	3	4	5
1st PHASE						
Temperature	°C	70	70	70	70	70
Pressure	ate	31	31	31	31	31
Time	min	30	20	30	30	30
H ₂ in gas phase	%mol	0.58	0.10	0.30	0.49	0.22
Ethylene in gas phase	%mol	1.45	2.60	2.50	1.96	1.70
Ethylene in pol.	%wt	3.0	4.3	4.1	3.8	3.9
Intr. Visc.	dl/g	2.18	3.09	2.31	2.54	2.72
Sol. Xyl. (S _A)	%wt	9.4	9.0	10.7	11.0	12.5
Ethylene in Sol. Xyl. (C _A)	%wt	11	16	17	22	20
Intr. Visc. Sol. Xyl. (I.V. _A)	dl/g	1.15	1.39	1.19	1.28	1.32
2nd PHASE						
Temperaure	°C	50	50	50	50	50
Pressure (gauge)	at	11.3	11.5	11.3	11.3	11.3
Time	min	335	500	250	250	260
H ₂ in gas phase	%mol	2.23	3.0	2.05	2.2	2.1
Ethylene in gas phase	%mol	15.9	16.9	22.54	18.65	18.9

TABLE 1B

EXAPLES	1	2	3	4	5
FINAL PRODUCT					
Yield	11	16.3	9.9	8.0	9.1
Comonomer	24.6	22.7	29.0	22.6	25.5
Bipolymer (B+C)	70	67	71.8	57	66
Intr. Visc.	2.05	2.3	2.34	2.42	2.4
Sol. in Xyl. (S _F)	63.4	60.5	63.5	51.3	60.5
Ethylene sol. Xyl. (C _F)	30.2	27.0	34.8	31.2	31.4
In. Vis. sol. Xyl. I.V.SF	1.83	2.02	2.12	1.83	1.98
Fraction B	9.45	9.37	11.34	10.4	9.75
Fraction C	60.55	57.63	60.46	46.6	56.15
Ethylene frac. (B)	51.9	57.1	53.7	52.9	59.8
Ethylene frac. (C)	31.1	27.6	35.7	32.1	32.3
In. Vis. frac. (C) (I.V.C)	1.86	2.05	2.18	1.89	2.03
Melting point	150	147	145	144	144
Flexural modulus	30	77	82	106	120
Notched IZOD at -50°C	DB	DB	DB	DB	DB
Shore D hardness	24	25	20	29	24
Tension Set at 75%	41	28	36	45	38
Tensile stress	13.8	15.8	15.4	17.3	16.4
Tens. str. at yield	5.0	5.8	4.6	15.5	6.1
Elongation at break	517	925	940	410	892
Haze	31	34	35	36	36
Vitreous trans. 1)	-25 (P)	-23 (P)	-28 (P)	-31 (P)	n.d.
	-75	-119	-81	-2	
	-128		-121	-125	

1) (P) = main peak
DB= does not break

Claims

1. A polyolefin composition comprising:

- A) 10-50 parts by weight of a homopolymer of propylene with isotactic index greater than 80, or a copolymer of propylene with ethylene, a $\text{CH}_2 = \text{CHR}$ α -olefin where R is a 2-8 carbon alkyl radical or combinations thereof, which copolymer contains over 85% by weight of propylene;
- B) 5-20 parts by weight of a copolymer fraction containing ethylene, insoluble in xylene at ambient temperature;
- C) 40-80 parts by weight of a copolymer fraction of ethylene and propylene or another $\text{CH}_2 = \text{CHR}$ α -olefin, where R is a 2-8 carbon alkyl radical, or combinations thereof, and, optionally, minor portions of a diene, said fraction containing less than 40% by weight of ethylene, being soluble in xylene at ambient temperature, and having an intrinsic viscosity from 1.5 to 4 dl/g;

the percent by weight of the sum of the (B) and (C) fractions with respect to the total polyolefin composition being of from 50% to 90% and the (B)/(C) weight ratio being lower than 0.4.

2. The polyolefin composition of claim 1, wherein the composition is in spheroidal particle form having an average diameter from 0.5 to 7 mm.
3. The polyolefin composition of claim 1 or 2, wherein the total content of copolymerized ethylene is from 15% to 35% by weight.
4. The polyolefin composition of one or more of the preceding claims, wherein the flexural modulus is less than 150 MPa, tension set at 75% is from 20% to 40%, and haze is less than 40%.
5. A process for the preparation of the composition of one or more of claims 2 to 4, comprising a first stage of polymerization of propylene, or mixtures thereof, with ethylene or another $\text{CH}_2 = \text{CHR}$ α -olefin, where R is a C_2 - C_8 alkyl radical, or combinations thereof, to form polymer component (A), and one or more stages of polymerization of mixtures of ethylene and propylene or said another α -olefin, or combinations thereof, optionally containing a diene, to form polymer components (B) and (C), using catalysts obtained from an Al-trialkyl compound and a solid component comprising a Ti halide or halogen-alcoholate and an electron-donor compound supported on anhydrous magnesium chloride, said solid component having a surface area of less than $100 \text{ m}^2/\text{g}$, a porosity from 0.2 to 0.4 cc/g , a pore volume distribution such that more than 50% of the pores have a radius greater than 100 \AA , and having an X-ray spectrum with a halo whose maximum intensity is between angles 2θ of 33.5° , and 35° , and no reflections at 2θ of 14.95° .
6. The process of claim 5, wherein the first stage of the polymerization is carried out in liquid monomer, and the subsequent stage, or stages, are carried out in gas phase.
7. The process of claim 5, wherein all stages are carried out in gas phase.
8. An article comprising the polyolefin composition of claim 1.

Patentansprüche

1. Polyolefin-Zusammensetzung, umfassend
 - (A) 10 bis 50 Gew. Teile eines Homopolymeren von Propylen mit einem Isotaktizitätsindex von höher als 80 oder eines Copolymeren von Propylen mit Ethylen, einem $\text{CH}_2 = \text{CHR}$ - α -Olefin, worin R für einen C_2 - C_8 -Alkylrest steht, oder Kombinationen hiervon, wobei dieses Copolymere über 85 Gew.% Propylen enthält;
 - (B) 5 bis 20 Gew. Teile einer Ethylen enthaltenden Copolymerfraktion, die bei Raumtemperatur in Xylol unlöslich ist;
 - (C) 40 bis 80 Gew. Teile einer Copolymerfraktion von Ethylen und Propylen oder einem anderen $\text{CH}_2 = \text{CHR}$ - α -Olefin, worin R für einen C_2 - C_8 -Alkylrest steht, oder Kombinationen hiervon und gegebenenfalls geringeren Anteilen eines Diens, wobei diese Fraktion weniger als 40 Gew.% Ethylen enthält, in Xylol bei Raumtemperatur löslich ist und eine innere Viskosität von 1,5 bis 4 dl/g besitzt; wobei der Gewichtsprozentanteil der Summe der (B)- und (C)-Fraktionen im Hinblick auf die Polyolefin-Gesamtzusammensetzung von 50 bis 90% beträgt und das (B)/(C)-Gewichtsverhältnis geringer als 0,4 ist.
2. Polyolefin-Zusammensetzung gemäß Anspruch 1, worin die Zusammensetzung in Form von sphäroidalen Teilchen mit einem durchschnittlichen Durchmesser von 0,5 bis 7 mm vorliegt.
3. Polyolefin-Zusammensetzung gemäß Anspruch 1 oder 2, worin der Gesamtgehalt an copolymerisiertem Ethylen 15 bis 35 Gew.% beträgt.
4. Polyolefin-Zusammensetzung gemäß einem oder mehreren der vorhergehenden Ansprüche, worin der Biegemodul geringer als 150 MPa, die bleibende Verformung bei 75% von 20% bis 40% beträgt und der Haze-Wert geringer als 40% ist.

5. Verfahren zur Herstellung der Zusammensetzung gemäß einem oder mehreren der Ansprüche 2 und 4, umfassend eine erste Stufe der Polymerisation von Propylen oder Mischungen hiervon mit Ethylen oder einem anderen $\text{CH}_2 = \text{CHR}-\alpha$ -Olefin, worin R für einen C_2 - C_8 -Alkylrest steht, oder von Kombinationen hiervon zur Bildung einer Polymerenkomponente (A) und eine oder mehrere Stufen einer Polymerisation von Mischungen von Ethylen und Propylen oder dieses weiteren α -Olefins oder von Kombinationen hiervon, gegebenenfalls ein Dien enthaltend, zur Bildung von Polymerkomponenten (B) und (C) unter Verwendung von Katalysatoren, erhalten aus einer Al-trialkylverbindung und einer festen Komponente, umfassend ein Ti-halogenid oder Halogenalkoholat und eine Elektronen-Donorverbindung, trägergestützt auf einen wasserfreien Magnesiumchlorid, wobei diese feste Komponente eine spezifische Oberfläche von geringer als $100 \text{ m}^2/\text{g}$, eine Porosität von 0,2 bis 0,4 ccm/g , eine Porenvolumenverteilung derart, daß mehr als 50% der Poren einen Radius von mehr als 100 \AA aufweisen, besitzt und ein Röntgenbeugungsspektrum mit einem Halo besitzt, dessen Intensitätsmaximum zwischen den Winkeln 2θ von $33,5^\circ$ und 35° liegt und ohne Reflexionen bei 2θ von $14,95^\circ$.
6. Verfahren gemäß Anspruch 5, worin die erste Stufe der Polymerisation in flüssigem Monomeren durchgeführt wird und die zweite Stufe oder Stufen in der Gasphase durchgeführt werden.
7. Verfahren gemäß Anspruch 5, worin alle Stufen in der Gasphase durchgeführt werden.
8. Erzeugnis, enthaltend die Polyolefin-Zusammensetzung gemäß Anspruch 1.

Revendications

1. Composition de polyoléfine comprenant:
- A) 10 à 50 parties en poids d'un homopolymère de propylène présentant un indice isostatique supérieur à 80, ou d'un copolymère de propylène et d'éthylène, d'une α -oléfine de formule $\text{CH}_2 = \text{CHR}$, dans laquelle R représente un radical alkyle comportant 2 à 8 atomes de carbone, ou une combinaison de ces composés, lequel copolymère contient plus de 85% en poids de propylène;
- B) 5 à 20 parties en poids d'une fraction de copolymère contenant de l'éthylène, insoluble dans le xylène à la température ambiante;
- C) 40 à 80 parties en poids d'une fraction de copolymère d'éthylène et de propylène, ou d'une autre α -oléfine de formule $\text{CH}_2 = \text{CHR}$, dans laquelle R représente un radical alkyle en C_2 à C_8 , ou une combinaison de ces produits, et éventuellement des proportions mineures d'un diène, ladite fraction contenant moins de 40% en poids d'éthylène, qui est soluble dans le xylène à la température ambiante, et présentant une viscosité intrinsèque de 1,5 à 4 dl/g;
- le pourcentage en poids de la somme des fractions (B) et (C) par rapport à la composition polyoléfinique totale représentant de 50 à 90% et le rapport pondéral (B)/(C) étant inférieur à 0,4.
2. La composition polyoléfinique selon la revendication 1, dans laquelle la composition est sous la forme de particules stéroïdes présentant un diamètre moyen de 0,5 à 7 mm.
3. La composition polyoléfinique selon la revendication 1 ou 2, dans laquelle la teneur totale en éthylène copolymérisé représente 15 à 35% en poids.
4. La composition polyoléfinique selon l'une quelconque des revendications précédentes, dans laquelle le module de flexion est inférieur à 150 MPa, la déformation rémanente à 75% est de 20% à 40%, et la turbidité est inférieure à 40%.
5. Un procédé de préparation de la composition selon l'une quelconque des revendications 2 à 4, comprenant une première étape de polymérisation de propylène, ou d'un mélange de ce dernier avec de l'éthylène ou une autre α -oléfine de formule $\text{CH}_2 = \text{CHR}$, dans laquelle R représente un radical alkyle en C_2 à C_8 , ou des combinaisons des ces produits, pour former un composant polymère (A), et une ou plusieurs étapes de polymérisation de mélanges d'éthylène comprenant de l'éthylène et du propylène ou ladite autre α -oléfine, ou des combinaisons de ces produits, contenant éventuellement un diène, pour former les composants polymères (B) et (C), en utilisant les catalyseurs obtenus à partir d'un dérivé trialkylaluminium et d'un composant solide comprenant un halogénure de Ti ou un alcoolate halogéné et un composé donneur d'électron supporté sur du chlorure de magnésium anhydre, ledit composant solide présentant une surface spécifique inférieure à $100 \text{ m}^2/\text{g}$, une porosité de 0,2 à 0,4

cm³/g, une distribution volumique des pores telles que plus de 50% des pores présentent un rayon supérieur à 100 angstroems, et présentant un spectre de diffraction aux rayons X présentant un halo dont l'intensité maximale est située entre les angles 2θ présentant une valeur de 33,5° et 35° et aucune réflexion à un angle 2θ présentant une valeur de 14,95°.

5

6. Le procédé selon la revendication 5, dans lequel la première étape de polymérisation est mise en oeuvre dans un monomère liquide et l'étape ultérieure ou les étapes ultérieures sont mises en oeuvre en phase gazeuse.

10

7. Le procédé selon la revendication 5, dans lequel toutes les étapes sont mises en oeuvre en phase gazeuse.

8. Un article comprenant la composition polyoléfinique selon la revendication 1.

15

20

25

30

35

40

45

50

55